

PRODUCT INFORMATION

A PRODUCT OF AMERICAN CHEMICAL TECHNOLOGIES, INC.



DuraLife P HS

High Performance High Temperature State of the Art Polyurea Based Grease

DESCRIPTION:

DuraLife P HS is a premium, high temperature, extreme pressure, multi-purpose, polyurea thickened grease. **DuraLife P HS** is manufactured with a high quality base oil with multiple types of viscosity index improvers, increasing its "body" and "tackiness" properties. This premium base oil preparation gives the grease a strong and long lasting body with a texture that can stand up to the toughest of applications. After the base oil formula is prepared, the grease is thickened using polyurea.

BENEFITS:

DuraLife P HS exhibits excellent thermal stability to extreme high and low temperatures and superior shear stability when compared to typical polyurea greases. **DuraLife P HS** has very good water resistance and will not wash out maintaining its consistency under severe working conditions and resisting rust and oxidation.

PROPERTIES:

	Test Method	DLP HS-0	DLP HS-1	DLP HS-2
Appearance		Smooth	Smooth	Smooth
Color		Green	Green	Green
Thickener Type		Polyurea	Polyurea	Polyurea
Thickener Content		6-9 %	6-9 %	6-9 %
NLGI Grade	ASTM D4950	00	1	2
Base Oil Viscosity @ 40 °C	ASTM D445	653 cSt	653 cSt	653 cSt
Base Oil Viscosity @ 100 °C	ASTM D445	36.9 cSt	36.9 cSt	36.9 cSt
Viscosity Index	ASTM D2270	92	92	92
US Steel Grease Mobility	USSMethodLT37		0.2 g/min	
@ 0 °F			1.7 g/min	
@ 20 °F				
Dropping Point	ASTM D566	246 °C (475 °F)	269 °C (517 °F)	260+ °C (500+ °F)
Cone Penetration @ 25 °C	ASTM D217			
Worked 60 strokes		400-430 dmm	324 dmm	265 dmm
Worked 10,000 strokes			335 dmm	
Worked 100,000 strokes			354 dmm	
DI Rust Protection, 48 hr, 52 °C	ASTM D1743	Pass	Pass	Pass
Oxidation Stability by OPV	ASTM D942	3 psi	3 psi	
Shell Roll Stability, 2 hr, 20-35 °C	ASTM D1831		4.18 % change	
Oil separation	ASTM D1742		0.4 %	

	Test Method	DLP HS-0	DLP HS-1	DLP HS-2
EP Properties (Four-Ball Method)	ASTM D2596			
Weld Point		315 kgf	315 kgf	500+ kgf
Load-Wear Index			55 kgf	
OK Load (Timken Method)	ASTM D2509	55 lb-f	55 lb-f	60 lb-f
Four-Ball Wear	ASTM D2266	0.45 mm	0.45 mm	0.45 mm
Low Temperature Torque, 1 min/-40°C	ASTM D4693		11.2 Nm	
High Temperature Torque, 1000 rpm, 160°C	ASTM D3527		120 h	
Combo Testing, % overall change	BSC		2.1	

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence, or otherwise is limited to the purchase price of the material. Freedom to use any patent owned by American Chemical Technologies' or others is not to be inferred from any statement contained herein.