

PRODUCT INFORMATION

A PRODUCT OF AMERICAN CHEMICAL TECHNOLOGIES, INC.



DuraLife P3500-00

High Performance High Temperature State of the Art Polyurea Based Grease

DESCRIPTION:

DuraLife P3500-00 is a premium, high temperature, extreme pressure, multi-purpose, polyurea thickened grease. **DuraLife P3500-00** is manufactured with a high quality base oil with multiple types of viscosity index improvers, increasing its "body" and "tackiness" properties. This premium base oil preparation gives the grease a strong and long lasting body with a texture that can stand up to the toughest of applications. After the base oil formula is prepared, the grease is thickened using polyurea.

BENEFITS:

DuraLife P3500-00 exhibits excellent thermal stability to extreme high and low temperatures and superior shear stability when compared to typical polyurea greases. **DuraLife P3500-00** has very good water resistance and will not wash out maintaining its consistency under severe working conditions and resisting rust and oxidation.

PROPERTIES:

	Test Method	DLP3500-00
Appearance		Smooth
Color		Green
Thickener Type		Polyurea
Thickener Content		6-9 %
NLGI Grade	ASTM D4950	00
Base Oil Viscosity @ 104 °F	ASTM D445	2,795-3,260 SUS
Base Oil Viscosity @ 212 °F	ASTM D445	150 SUS
Viscosity Index	ASTM D2270	92
Dropping Point	ASTM D566	246 °C (475 °F)
Cone Penetration @ 25 °C	ASTM D217	
Worked 60 strokes		400-430 dmm
DI Rust Protection, 48 hr, 52 °C	ASTM D1743	Pass
Oxidation Stability by OPV	ASTM D942	3 psi
EP Properties (Four-Ball Method)	ASTM D2596	
Weld Point		315 kgf
OK Load (Timken Method)	ASTM D2509	55 lb-f
Four-Ball Wear	ASTM D2266	0.45 mm

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence, or otherwise is limited to the purchase price of the material. Freedom to use any patent owned by American Chemical Technologies' or others is not to be inferred from any statement contained herein.